



## 60-90/91 Foster Monolar<sup>®</sup> Mastic

### Colour

60-90 White  
60-91 Grey

### Application Consistency

Trowel or glove

### Average Weight/ U.S. Gallon (ASTM D 1475)

10.0 to 10.4 lbs (1.20 to 1.25 kg)

### Average Non-Volatile (ASTM D 1644)

42% by volume (60% by weight)

### Coverage Range (FSTM 72)

(Subject to the nature of material coated.)

Wet coverages shown below are for smooth non-porous surfaces. Porous or rough surfaces will require more material to attain required dry thickness.

### Dry Thickness:

0.034 inch (0.9 mm)

### Equivalent Wet Coverage:

0.080 inch (2.0 mm) 5 gal/100 sq. ft.  
(2.0 to 2.4 l/m<sup>2</sup>)

### Drying Time 73°F (23°C) 50% RH (ASTM D 1640)

Set to Touch : 3 hours

Dry Touch : 48 hours

### Service Temperature Limits (FSTM 70)

(Temperature at coated surface)

Minus 50°F to 220°F (-46°C to 104°C)

### Water Vapour Permeance

ASTM E 96, Method E, 0.025 perms (0.016 metric (perms) at 51 mils dry (1.3 mm)

ASTM F-1249, 0.03 perms (0.02 metric perms) at 30 mils dry (0.76 mm) (Tested at 100°F and 90% relative humidity differential)

### Wet Flammability (ASTM D 3278)

Flash point 110°F (43°C)

### Surface Burning Characteristics (ASTM E 84)

Flame Spread : 10

Smoke Developed : 15

Tested at coverage rate of 25 sq. ft./gal. (0.61 m<sup>2</sup>/l). Applied to ¼ inch (6.4 mm) inorganic reinforced cement board. The flame spread may vary at different product thicknesses and/ or when applied over other surfaces.

**Foster Monolar Mastic** is a tough, flexible, and fire-resistive elastomeric finish for protection of outdoor thermal insulation. It contains DuPont Hypalon\* rubber. It's an excellent vapour barrier for low temperature insulation on tanks, pipework, vessels and fittings.

**Monolar Mastic** provides outstanding weather barrier protection, showing good colour retention, excellent chemical resistance, and durability.

**Monolar Mastic** trowels easily and smoothly without drag or excessive stringing. It features higher than average volume solids, reducing the number of gallons that need to be applied.

**Monolar Mastic** is produced under the classification and follow-up service of Underwriter's Laboratories, Inc.

**Monolar Mastic** meets NFPA 90A and 90B 25/50 requirements.

**Monolar Mastic** contains no asbestos, lead, mercury, or mercury compounds.

### Limitations

Store and apply between 40°F (4°C) and 100°F (38°C).

Always test plastic materials for compatibility when using a solvent base product.

Outdoor horizontal surfaces must always drain completely. A pitch of at least ¼" per foot (2 cm/m) is recommended.

Make certain this product is completely dry and the area free from solvent odour if food is involved.

Select Monolar Coating 60-95 (white) or 60-96 (gray) for airless spray or brush application. PE/PC-BM

**FSTM:** Foster Standard Test Method

® Trademark of Foster Products Corporation \*

Trademark of E.I. DuPont Company



## FOSTER MONOLAR<sup>®</sup> MASTIC 60-90 / 60-91

### Material Preparation

Stir well. DO NOT THIN. Apply only to clean dry surfaces. Keep container closed when not in use to prevent solvent evaporation.

### Application

To prevent water vapour and moisture infiltration, proper and complete flashing is required. Follow flashing specifications.

### Normal Service

Apply a tack coat of MONOLAR Mastic at a thickness of 1/32 inch (0.8 mm). This is equivalent to 2 gal./100 sq. ft. (0.8 l/m<sup>2</sup>). Embed Foster MAST-A-FAB<sup>®</sup> white membrane into wet tack coat. Smooth membrane to avoid wrinkles and overlap all seams at least 2 inches (5 cm). Apply a finish coat of MONOLAR Mastic at a minimum thickness of 3/64 inch (1.2 mm). This is equivalent to 3 gal./100 sq. ft. (1.2 l/m<sup>2</sup>). This finish coat shall be applied no later than 2 hours after the tack coat and shall completely cover membrane. This application shall provide a minimum dry film thickness of 34 mils (0.9 mm).

### Severe and Cryogenic Service

Increase the tack coat coverage to 3 gal./100 sq. ft. (1.2 l/m<sup>2</sup>) and the finish coat to 4 gal./100 sq. ft. (1.6 l/m<sup>2</sup>). Allow the tack coat to set up before applying the finish coat on vertical surfaces. This application shall provide a minimum dry film thickness of 51 mils (1.3 mm).

### Trowel

Use clean tools. Work in long even strokes to insure uniform thickness. Wet tool with detergent foam (not soap) occasionally to prevent a build up of dried mastic.

### Rubber Glove

Best appearance may be achieved by smoothing wet MONOLAR Mastic with detergent foam (not soap) on clean glove or brush, being careful not to pick up any MONOLAR Mastic on glove or brush.

### Clean-Up

Use xylol (flammable) or chlorinated solvent (non-flammable) for cleaning equipment. Dried MONOLAR Mastic is extremely difficult to remove.

### Data Reproduced From Underwriters' Laboratories, Inc. Building Materials Directory Coating, General Purpose R3593 H.B. Fuller Company

#### Surface Burning Characteristics

Surface	¼ inch (6.4 mm) Inorganic Surface Reinforced Cement Board
Flame Spread	10
Smoke Developed	15
Number of Coats	1
Rate Per Coat (sq. ft. per gal.)	25

### For industrial use only.

This data sheet is based on specifications, data and test results available to us at the time of publication.

In the course of time changes herein may (have) take(n) place. No guarantee as to completeness, accuracy or results is either expressed or implied. The suitability to an intended use is the responsibility of the user. As material-choice, method of application and site conditions are beyond our control, we accept no liability for direct or consequential damages; our only obligation being to resupply ex our stores any material that is proved to be defective within the published\* shelf life.

\* If not applicable, within 6 months from date of supply.