



## TEMTEX™ 200/LS



Description	<b>A lightweight fiberglass fabric with a smooth, closed structure.</b>		
Applications	- Fire protection - "Lagging" fabric - Cover for fibrous insulation - Reinforcement fabric (or polyester/epoxy) , etc.		
Approvals			
Characteristics of Temtex 200/LS			Test method
Total weight	g / m <sup>2</sup>	200	± 5%
Width (std)	mm	1000	± 10
Thickness	mm	0.20	± 0.02
Roll length (std)	m	450	
Max. application temperature	°C	500	
Remarks			

Fabric structure				
	Unit	Data	Tolerance	Test method
<b>Base fabric</b>		E-Glass		
Weight	g / m <sup>2</sup>	200	± 4%	DIN 53854
Weave		Plain 1/1		
Setting	per cm	17.0 x 13.0	± 3%	DIN 53853
Warp	Tex	EC6-34 S x 2	± 5%	DIN 60850 T.2
Weft	Tex	EC9-68 S	± 5%	DIN 60850 T.2
Tensile strength (warp x weft)	N/cm	470 x 350		DIN 53857
<b>Coating / Finish</b>				
Weight	g / m <sup>2</sup>			
1 or 2 sided				

Tensile strength data refers to loomstate fabrics. Stability, thickness and surface weight vary according to the type of fabric finish. The given values are approximate and not guaranteed.