



TEMTEX™ 301/Rew.



Description	Lightweight “lagging” glass fabric, impregnated throughout with a proprietary inorganic adhesive, which is dispersible in water.			
Applications	- Pipe lagging, joints and valves.			
Approvals	MIL-C-20079H Type I, Class 4; USCG 164.009			
Characteristics of Temtex 301/Rew.				Test method
Total weight	g / m ²	510	± 5%	
Width	mm	1524	± 15	
Thickness	mm	0.90	± 0.1	
Roll length	m	45.72		
Max.application temperature	°C	232		
Remarks				

Fabric structure				
	Unit	Data	Tolerance	Test method
Base fabric		E-Glass		
Weight	g / m ²	300	± 5%	
Weave		Basket		
Setting	per cm	-		
Warp	Tex	18 x 16		
Weft	Tex	-		
Tensile strength (warp x weft)	N/cm	100 x 50		
Coating		Rewettable		
Weight	g / m ²	210	± 5%	
1 or 2 sided		2		

Tensile strength data refers to loomstate fabrics. Stability, thickness and surface weight vary according to the type of fabric finish. The given values are approximate and not guaranteed.