



TEMTEX™ T950/Cara



Description	A twill-woven texturized fabric, heat-cleaned (caramelized) to reduce dusting and to flash-off the weaving additives.			
Applications	- Insulation mattresses - Heat protection		- Base fabric for foil facings - Asbestos replacement, etc.	
Approvals				
Characteristics of Temtex T950/Cara				Test method
Total weight	g / m ²	945	± 5%	
Width (std)	mm	1000	± 15	
Thickness	mm	1.50	± 0.1	
Roll length (std)	m	50		
Max. application temperature	°C	500		
Remarks				

Fabric structure				
	Unit	Data	Tolerance	Test method
Base fabric		E-Glass		
Weight	g / m ²	950	± 5%	DIN EN 12127
Weave		Twill 2/2		
Setting	per cm	11.0 x 7.5	± 3%	DIN 53853
Warp	Tex	ET6-500 tex	± 5%	
Weft	Tex	ET6-500 tex	± 5%	
Tensile strength (warp x weft)	N/cm	1100 x 800		DIN 53857
Coating / Finish		Caramelized		
Weight	g / m ²	-		
1 or 2 sided				

Tensile strength data refers to loomstate fabrics. Stability, thickness and surface weight vary according to the type of fabric finish. The given values are approximate and not guaranteed.