



TEMTEX™ T950/HT600



Description	Texturised glass fabric with a high-temperature finish.			
Applications	- Insulation mattresses - Etc. - Compensators			
Approvals				
Characteristics of Temtex T950/HT600				Test method
Total weight	g / m ²	960	± 5%	
Width (std)	mm	1000	± 15	
Thickness	mm	1.45	± 0.1	
Roll length (std)	m	50		
Max. application temperature	°C	600		
Remarks				

Fabric structure				
	Unit	Data	Tolerance	Test method
Base fabric		E-Glass		
Weight	g / m ²	950	± 5%	DIN EN 12127
Weave		Crowfoot Satin		
Setting	per cm	11.0 x 7.5	± 3%	DIN 53853
Warp	Tex	ET6-500 tex	± 5%	
Weft	Tex	ET6-500 tex	± 5%	
Tensile strength (warp x weft)	N/cm	1100 x 800		DIN 53857
Coating / Finish		High temp. treated		
Weight	g / m ²	10	± 5%	
1 or 2 sided		2		

Tensile strength data refers to loomstate fabrics. Stability, thickness and surface weight vary according to the type of fabric finish. The given values are approximate and not guaranteed.